

CLASSIFICATION OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH BS EN 13501-1:2018

Test Sponsor:

Alstone Manufacturing Pvt. Ltd.
15th Floor, Vijaya Building,
17, Barakhamba Road, Connaught Place
New Delhi-110001, India
T: +91-011-41232400
Website: www.alstoneindia.com

Test Material:

4mm thick 'Alstone® Zinc FR B' Zinc Composite Panel



**THOMAS BELL-WRIGHT
INTERNATIONAL CONSULTANTS**

Issue Date: 5-Oct-22
Classification Report Reference No: WH149-3

PO BOX 26385, DUBAI UAE

T +971 (0)4 821 5777

fire@bell-wright.com

www.bell-wright.com

DUBAI

DOHA

RIYADH



Accreditation

Testing

ISO/IEC 17025: General requirements for the competence of testing and calibration laboratories with:

United Kingdom Accreditation Service (UKAS) - Testing Laboratory: **4439**

www.ukas.com



Memberships

Members of European Group of Organization for Fire Testing, Inspection and Certification

www.egolf.org.uk

Member of Association for Specialist Fire Protection

www.asfp.org.uk

Member of Centre for Window and Cladding Technology

www.cwct.co.uk



The work which is the subject of this report falls under the accreditations of **ISO 17025 UKAS**.



Table of Contents

1. INTRODUCTION	4
2. SPONSOR.....	4
3. MANUFACTURER.....	4
4. TESTING LABORATORY	4
5. DETAILS OF CLASSIFIED PRODUCT	4
6. SPECIMEN PREPARATION PROCEDURE.....	6
7. REPORT & TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION	6
7.1. Reports.....	6
7.2. Results.....	6
8. CLASSIFICATION & FIELD OF APPLICATION	7
8.1. Reference of classification	7
8.2. Classification	7
8.3. Field of application.....	7
9. LIMITATIONS	8
10. ANNEXURE A	9



1. INTRODUCTION

This classification report defines the classification assigned to 4mm thick 'Alstone® Zinc FR B' Zinc Composite Panel in accordance with the procedures given in BS EN 13501-1:2018: Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests.

2. SPONSOR

Name: Alstone Manufacturing Pvt. Ltd.
Address: 15th Floor, Vijaya Building,
17, Barakhamba Road, Connaught Place
New Delhi-110001, India
T: +91-011-41232400
Website: www.alstoneindia.com

3. MANUFACTURER

Name: Alstone Manufacturing Pvt. Ltd.
Address: Khasra No: 1393, Langha Road Industrial Area
Village Chharba, P.O. Sahaspur, Dehradun 248197
Uttarakhand, India

4. TESTING LABORATORY

Name: Thomas Bell-Wright International Consultants (TBWIC)
Address: Corner of 46th and 47th Streets,
Jebel Ali Industrial Area 1
Dubai, UAE
T: T: +971 04 821 5777
Website: www.bell-wright.com

5. DETAILS OF CLASSIFIED PRODUCT

Note: The testing laboratory does not hold any responsibility for the information that has been provided by the test sponsor which could not be verified by the testing laboratory, as this could affect the validity of the test result. All information that could not be verified will be indicated by an asterisk () mark.*

Product Description		4mm thick Zinc Composite Panel*	
Product Reference		Alstone® Zinc FR B*	
Manufacturer		Alstone Manufacturing Pvt. Ltd.*	
Thickness		4mm* (stated) 4.17mm (measured by TBWIC)	
Area Weight of Product		9.5 ± 0.5 kg/m ² * (stated) 9.9 kg/m ² (measured by TBWIC)	
Product Details	Topcoat (Fire Exposed Face)	Material	Quartz pigment treated (Pre-patinated)*
		Manufacturer	VMZINC Citi Solutions - India*
		Thickness	22-25µm* (stated)



		Colour	Matt Grey Patina*
		Area Weight	0.16 kg/m ² * (stated)
	Metal Top Skin	Description	Zinc Alloy*
		Manufacturer	VMZINC*
		Alloy	Z20*
		Thickness	0.5mm* (stated)
		Density	7310 kg/m ³ * (stated)
		Adhesive	Material
	Manufacturer		Ecoplast*
	Thickness		80µm* (stated)
	Area Weight		0.075 kg/m ² * (stated)
	Density		940 kg/m ³ * (stated)
	Core	Material	FR B Core*
		Manufacturer	Carbo Industries*
		Thickness	3.1mm* (stated)
		Area Weight	4.8 kg/m ² * (stated)
		Density	1800 kg/m ³ * (stated)
	Adhesive	Material	Polyfine film*
		Manufacturer	Ecoplast*
		Thickness	80µm* (stated)
		Area Weight	0.075 kg/m ² * (stated)
		Density	940 kg/m ³ * (stated)
	Metal Bottom Skin	Material	Aluminium*
		Manufacturer	DEJU*
		Alloy	AA3003 H16* (stated)
		Thickness	0.5mm* (stated)
		Density	2710 kg/m ³ * (stated)
	Back coat	Material	PE Service Coat*
		Manufacturer	DEJU*
		Thickness	5-8µm* (stated)
		Area Weight	0.007 kg/m ² * (stated)
Exposed Face		Coated Zinc face (verified by TBWIC)	



6. SPECIMEN PREPARATION PROCEDURE

The choice, design and definition of the specimen have been made by Alstone Manufacturing Pvt. Ltd., and TBWIC Testing Laboratory has not been involved in the selection or design of the specimen. The results apply to the samples as received.

Note: There are contexts where information has been provided by the sponsor and verification of information has been done through either technical datasheet or other document submission, or as indicated directly by the sponsor. For this reason, materials have been tested in an as-received condition and TBWIC bears no liability for the legitimacy of the submitted information.

7. REPORT & TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION

7.1. Reports

Name of Laboratory	Test Sponsor	Test Report No.	Test Method/Field of Application Rules
Thomas Bell-Wright International Consultants (TBWIC)	Alstone Manufacturing Pvt. Ltd.	WH149-1	BS EN 13823:2020
		WH149-2	BS EN ISO 11925-2:2020

7.2. Results

Test Method	TEST PARAMETERS	No. of tests	TEST RESULTS	
			Continuous parameter-mean (m)	Compliance parameters
BS EN ISO 11925-2:2020	$F_s \leq 150\text{mm}$ within 60 seconds	12	$F_s \leq 150\text{mm}$	Compliant
	Ignition of filter paper		Nil	Compliant

Test Method	TEST PARAMETERS	No. of tests	TEST RESULTS	
			Continuous parameter-mean (m)	Compliance parameters
BS EN 13823:2020	$\text{FIGRA}_{0.2\text{MJ}} \leq 120 \text{ W/S}$	3	57	Compliant
	$\text{THR}_{600\text{s}} \leq 7.5 \text{ MJ}$	3	5.0	Compliant
	Lateral Flame Spread < Edge of Specimen	3	< Edge of Specimen	Compliant
	CRITERIA for subclass "s1"			
	$\text{SMOGR}_A \leq 30 \text{ m}^2/\text{s}^2$ <i>Note1</i>	3	1	Compliant
	$\text{TSP}_{600\text{s}} \leq 50 \text{ m}^2$ <i>Note1</i>	3	11	Compliant
	CRITERIA for subclass "d0"			
	Flaming droplets/particles within 600s	3	Nil	Compliant

Note 1: Corrected value as per ANNEX A, Clause A.6.1.2 of BS EN 13823:2020.



8. CLASSIFICATION & FIELD OF APPLICATION

8.1. Reference of classification

This classification has been carried out in accordance with Clause 8 of EN 13501-1:2018.

8.2. Classification

The product, 4mm thick 'Alstone® Zinc FR B' Zinc Composite Panel in relation to its reaction to fire behavior are classified;

Fire behavior		Smoke production			Flaming droplets	
B	-	s	1	,	d	0

Reaction to fire classification: B – s1, d0

Remark: The classes with their corresponding fire performance are given in annex A.

8.3. Field of application

This classification is valid for the following end use applications:

- Construction applications

This classification is also valid for the following product parameters:

Overall product thickness	No variation allowed
Product density	No variation allowed
Product composition	No variation allowed
Colour	No variation allowed
Joints	Results valid for material with or without vertical & horizontal joints of $\leq 15\text{mm}$



9. LIMITATIONS

This document does not represent type approval or certification of the product.

This report and all records of the test to which it relates may be not be retained by TBWIC further than 5 years from the date of testing.

This test report is respectfully submitted by: Thomas Bell-Wright International Consultants

Prepared by:

Sam Sancho Thomas
Fire Testing Engineer

Reviewed and Approved by:

Suketa Tyagi
Manager – Reaction to Fire



Report Revision Tracking		
Revision No.	Date Issued	Notes & Amendments
Rev.00	05-Oct-22	This is the first issue of the report. No revisions are included.



10. ANNEXURE A

Classes of reaction to fire performance for construction products excluding floorings and linear pipe thermal insulation products

Class	Test method(s)	Classification criteria	Additional classification
A1	EN ISO 1182 ^a and	$\Delta T \leq 30\text{ }^{\circ}\text{C}$; and $\Delta m \leq 50\%$; and $t_f = 0$ (i.e. no sustained flaming)	-
	EN ISO 1716	$PCS \leq 2,0\text{ MJ/kg}^a$ and $PCS \leq 2,0\text{ MJ/kg}^{b,c}$ and $PCS \leq 1,4\text{ MJ/m}^2^d$ and $PCS \leq 2,0\text{ MJ/kg}^e$	-
A2	EN ISO 1182 ^a or	$\Delta T \leq 50\text{ }^{\circ}\text{C}$; and $\Delta m \leq 50\%$; and $t_f \leq 20\text{ s}$	-
	EN ISO 1716 and	$PCS \leq 3,0\text{ MJ/kg}^a$ and $PCS \leq 4,0\text{ MJ/m}^2^b$ and $PCS \leq 4,0\text{ MJ/m}^2^d$ and $PCS \leq 3,0\text{ MJ/kg}^e$	-
	EN 13823	$FIGRA \leq 120\text{ W/s}$ and $LFS < \text{edge of specimen}$ and $THR_{600s} \leq 7,5\text{ MJ}$	Smoke production ^f and Flaming droplets/particles ^g
B	EN 13823 and	$FIGRA \leq 120\text{ W/s}$ and $LFS < \text{edge of specimen}$ and $THR_{600s} \leq 7,5\text{ MJ}$	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ : Exposure = 30 s	$F_s \leq 150\text{ mm}$ within 60 s	
C	EN 13823 and	$FIGRA \leq 250\text{ W/s}$ and $LFS < \text{edge of specimen}$ and $THR_{600s} \leq 15\text{ MJ}$	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ : Exposure = 30 s	$F_s \leq 150\text{ mm}$ within 60 s	
D	EN 13823 and	$FIGRA \leq 750\text{ W/s}$	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ : Exposure = 30 s	$F_s \leq 150\text{ mm}$ within 60 s	
E	EN ISO 11925-2 ⁱ : Exposure = 15 s	$F_s \leq 150\text{ mm}$ within 20 s	Flaming droplets/particles ^h
F	EN ISO 11925-2 ⁱ : Exposure = 15 s	$F_s > 150\text{ mm}$ within 20 s	

^a For homogeneous products and substantial components of non-homogeneous products.

^b For any external non-substantial component of non-homogeneous products.

^c Alternatively, any external non-substantial component having a $PCS \leq 2,0\text{ MJ/m}^2$, provided that the product satisfies the following criteria of EN 13823: $FIGRA \leq 20\text{ W/s}$, and $LFS < \text{edge of specimen}$, and $THR_{600s} \leq 4,0\text{ MJ}$, and $s1$, and $d0$.



^d For any internal non-substantial component of non-homogeneous products.

^e For the product as a whole.

^f In the last phase of the development of the test procedure, modifications of the smoke measurement system have been introduced, the effect of which needs further investigation. This may result in a modification of the limit values and/or parameters for the evaluation of the smoke production.

s1 = SMOGRA $\leq 30\text{m}^2/\text{s}^2$ and TSP_{600s} $\leq 50\text{m}^2$;

s2 = SMOGRA $\leq 180\text{m}^2/\text{s}^2$ and TSP_{600s} $\leq 200\text{m}^2$;

s3 = not s1 or s2

^g **d0** = No flaming droplets/ particles in EN 13823 within 600 s;

d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s;

d2 = not d0 or d1.

Ignition of the paper in EN ISO 11925-2 results in a d2 classification.

^h Pass = no ignition of the paper (no classification);

Fail = ignition of the paper (d2 classification).

ⁱ Under conditions of surface flame attack and, if appropriate to the end-use application of the product, edge flame attack.

---- End of Classification Report ----